

AQUACHOICE SPORT

Product Description

AQUACHOICE SPORT is a two-component, water-based hardwood-floor finish based on polyurethane especially for the use on sport floors. The suitability for its purpose is evidenced by a test certificate as per DIN 18032-2; Ö-Norm B 2608 ÖISS-Richtlinie 1990 and EN 14904. Due to its excellent resistances AQUACHOICE SPORT can also be used on heavy-traffic hardwood floors to which special requirements are made as to slip resistance.

Zertifikate / Zulassungen



Giscode:	W3/DD+
AbZ-Nr.	Z-157.10-47
FIBA:	matt
Suitability for sports floors:	DIN V 18032-2
Suitability for sports floors:	DIN EN 14904
Suitability for sports floors Austria:	Ö-Norm B2608
Slip resistance:	DIN 51130/DGVU 108-003 / R9
Fire class:	Cfl-s1 according to DIN EN 14342 if the wood is Cfl-s1 certified and up to 100 g/m ² of varnish has been used.
ATFA:	Compliant
NWFA:	Compliant
MFMA:	Compliant

Specifications/ Approvals

Components:	waterbased dispersions, according MSDS
Clarity:	translucent, dries clear
Scent:	unoffensive – amine
Body:	full
Texture:	richly smooth
Density:	8.65 lb/gal
Packaging:	1.45 gal + hardener
Sheen:	(measured at 60°)* matt / satin (10-20) semigloss (30-40)
Coverage:	510 – 800 sf/1,45 gal
Stability:	do not freeze
Leveling:	excellent
Defoaming:	excellent
Drying Time:	2 hrs.
Pot Life:	2 hrs.
Cure Time:	72 hrs, depending on climate conditions
Chemical Resistance:	excellent
Shelf Life:	15 months unopened
Flash Point:	N / A

For further details please refer to MSDS.

Recommended lacquer sequence

Priming is possible with AQUACHOICE FLEXPRIMER. For a more intense color, AQUACHOICE EXOBLOC or CLASSIC BASEOIL can also be used as primer.

AQUACHOICE SPORTMARKING COLOR is applied either before or on the last layer of AQUACHOICE SPORT.

Application Instructions

For professional use only.

Shortly before use AQUACHOICE SPORT is mixed 10:1 with AQUACHOICE Härter (hardener) in the combo can or in the BERGERTOOL MIXBOX. Mix well right after adding the hardener.

The mixture is good for 2 h (open time); although the mixture is liquid for about 1 day, because of declining resistances of the dried finish film after 2 h, it should not be used any more. Mix only as much material as you will need. The mixture releases CO₂ – so, to avoid the cans bursting, do not seal airtight.

Contrary to conventional solvent-based finishes, AQUACHOICE finishes should be applied in rich layers.

In order to avoid excessive swelling pressure, we recommend to do only one rolled coat of water-borne finish per day, so that the wood has enough time to release the absorbed water.

As a rule, the finish itself can be cautiously sanded and walked on after 3-4 h at 73,4°F/50% humidity. Insufficient ventilation, low temperature, different humidity as well as thicker finish coats will considerably delay the drying. Do not expose to wear, cover with carpets or apply care products for 7 days.

Maintenance and Care

Regular cleaning and care with compatible care products is essential for extended floor life and beauty. For best results, use BRILLIANCE CLEANER L94 for basic cleaning and tough stain removal. We recommend the installation of floor mats at each entry to keep out harmful dirt, mud and grit.

Storage / transport

Shelf life of original unopened packing min. 15 months (finish) resp. 15 months (hardener) provided that material is transported and stored at a cool and dry place protected from freezing. Partially used-up hardener cans must be sealed airtight.

Note on gymnasiums with sport floors

Please note that special conditions exist in gyms with sport-floors and these must be taken into account. For this reason, it is important that only 1 coat of water-based paint is applied per day. Due to the drying time of 24 h, the standard humidity of the wood will be reached once again with appropriate ventilation of the room. This method of operation ensures that damage to the parquet is prevented by extreme swelling. In addition, the detailed information in the respective Technical Data Sheets of the listed products must be observed.

AQUACHOICE SPORT

Safety Precautions

Avoid skin or eye contact and inhalation of vapors. Use with adequate ventilation. Wear protective gloves and eye / face protection. Wash thoroughly after handling. Keep unopened containers closed. Do not seal containers containing mixed product due to release of carbon dioxide.

Do not use for sputtering or spraying. Keep out of reach of children.

Residual quantities should not be poured into sewage water drains, but disposed of in compliance with local, state, and federal regulations.

For further details please refer to MSDS.

Description of first aid measures

If medical advice is needed, have product container or label at hand.

24-hour emergency number in side USA: +1 872 5888271

General information

In all cases of doubt, or when symptoms persist, seek medical advice. In case of unconsciousness give nothing by mouth, place in recovery position and seek medical advice.

In case of inhalation

Remove casualty to fresh air and keep warm and at rest. In case of irregular breathing or respiratory arrest provide artificial respiration.

Following skin contact

Take off immediately all contaminated clothing. After contact with skin, wash immediately with plenty of water and soap. Do not use solvents or thinners.

After eye contact

Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do, continue rinsing. Seek medical advice immediately.

Following ingestion

If swallowed, rinse mouth with water (only if the person is conscious). Seek medical advice immediately. Keep victim calm. Do NOT induce vomiting.

Most important symptoms and effects, both acute and delayed

In all cases of doubt, or when symptoms persist, seek medical advice.

Indication of any immediate medical attention and special treatment needed

First Aid, decontamination, treatment of symptoms.

Manufacturer's Recommendations

This Technical Data Sheet is based on extensive research and wide-ranging experience and is meant to assist you. Restrictive information and precautions have not been avoided in order to reduce risk of fault. Technical Data Sheets do not contain all applications or events that could occur with different species of wood, installation, techniques and finishing. Therefore, you cannot be released from the obligation to contact the manufacturer in cases of doubt, to make your own tests on site and to be critically attentive during the job process. The contents of this data sheet are not legally binding and do not establish any contractual legal relationship. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. This information is subject to change without further notice. Please read the instructions carefully before processing this product. This BERGER-SEIDLE® product must be processed by a qualified person for parquet laying, for whom this manual is intended. The activities shall be carried out in accordance with the rules of the craft, the state of the art and the applicable standards and regulations of the country in which the product is used (USA/CAN = NWFA // AUS = ATFA). The specifications of DIN 18356 "Parquet and wood paving" and DIN 18365 "Flooring work", information sheets and technical information of the TKB, the BEB, the CTA and the BVPF-Bundesverband Parkett & Fußboden-technik must be observed. The customer must be informed about the cleaning and care specifications of the product. Any use that does not conform to the scope of BERGER-SEIDLE®'s application is considered improper. The improper use and non-compliance with the instructions in this manual is largely the responsibility of the processor and as a result excludes the manufacturer's liability and warranty. Before using the product, the general conditions for use must be checked properly and professionally.

Cross reference

The following Technical Data Sheets should be observed:

- General instructions of use for hardwood floor finishing products
- Cleaning and maintenance of finished/oiled floors
- Identification and safety instructions (MSDS)

* The degree of gloss depends on the method of application, the substrate and the room climatic conditions.

**If the content of the Technical Data Sheet differs from other printed material, e.g. labels, the current version of the Technical Data Sheet on the homepage is always deemed valid. Printed material is always adapted when reprints are made.