

Expertise: 2101577-03-00-01ae

Datum / Date: 2021-05-10
KT

Client: Berger-Seidle GmbH, Maybachstraße 2, DE-67269 Grünstadt/Weinstr.

Order: Examination of materials

Order: 2021-02-17 K. Hoffmann

Receipt: 2021-02-22

Test item

as received: Test plate, AquaSeal ElasticStar with addition AquaSeal Antislip Add

Results of examination:

Testing of floor coverings - Determination of the anti-slip properties

DIN 51130

Parameter	Unit	Result
rectified medium angle of inclination	°	16,53
Category	-	R 10

Remark:

rectified medium angle of inclination	anti-slip category
6° - 10°	R 9
> 10° - 19°	R 10
> 19° - 27°	R 11

Assignment of the rectified medium angles of inclination to the anti-slip categories



Dipl.-Ing. (FH) L. Vijselaar
(Abteilungsleitung / Department Management)



Dr. K. Schulte
(Institutsleitung / Managing Director)



Die Prüfergebnisse beziehen sich ausschließlich auf die Prüfgegenstände. Ohne schriftliche Genehmigung des PFI darf die Expertise nicht auszugsweise verwendet werden. Bewertung erfolgt ohne Berücksichtigung der Messunsicherheit. Restliches Untersuchungsmaterial wird nach 10 Wochen vernichtet. In Einzelfällen kann eine Untervergabe an andere geeignete Prüflaboratorien erfolgen. Ein Verzeichnis der akkreditierten Prüfverfahren und unsere geltenden Allgemeinen Geschäftsbedingungen können auf unserer Internetseite eingesehen werden und werden Ihnen auf Anfrage gerne zugesandt. / Test results solely refer to the items tested. Extracts of the expertise may not be used without written permission by PFI. Rating does not consider the uncertainty of measurement. Remaining materials will be destroyed after 10 weeks. In individual cases, tests can be carried out by qualified subcontracting laboratories. A list of accredited test methods and our applying general terms and conditions are available on our website and will be sent to you on request.

Prüf- und Forschungsinstitut Pirmasens e.V. • Marie-Curie-Strasse 19 • D-66953 Pirmasens • www.pfi-germany.de • info@pfi-germany.de